Serial No. 09/803,941



present invention has a weaker outbreak tensile load in comparison with an outer circumferential wall portion of a normal ceramic honeycomb structure, thereby thermal shock resistance is increased, and rupture is hard to be caused.

IN THE CLAIMS:

Please amend claims 1 and 3 as follows.

Wall of the second of the seco

- 1. (Amended) A ceramic honeycomb structure comprising a plurality of through-holes surrounded by partition walls, wherein a thermal expansion coefficient of an outer circumferential wall portion in the ceramic honeycomb structure is larger than a thermal expansion coefficient, in a direction of a diameter, of an inside partition wall portion in the ceramic honeycomb structure, and stress is applied to the inside partition wall portion from the outer circumferential wall portion.
- Ky
- 3. (Amended) A ceramic honeycomb structure as defined in claim 1, wherein a partition wall of the ceramic honeycomb structure has a thickness of less than 0.1 mm.